



PRODUCT SPECIFICATIONS

Traction Tread

CONSTRUCTION

Material: Solid nitrile rubber

Thickness: 1/8 inch (0.125")

STANDARDS & TESTING

- Certified high-traction by the National Floor Safety Institute (NFSI)
- Passes flammability standard DOC-FF1-70
- Static decay test method 4046 federal standard 101B/NFPA 99 Chapter 12Section 4.1.3.8 (f)(3)(i) – maximum time recorded: 01 seconds
- ASTM C1028-96 static coefficient of friction:
 - Dry 0.92
 - Wet 0.86
- ESD rating of electrically conductive:
 - Surface to surface at 50% relative humidity 6.2×10^4 ohms
 - Surface to surface at 12% relative humidity 1.5×10^5 ohms
- Temperature use ASTM D 1056: cold crack -20 degrees F
- Melt point over 500 degrees F. Tested at temperatures up to 1800 degrees F for welding/slag resistance